



ANDALUSITE

RUN OF MINE GRADES

Andalusite has robust behavior in difficult conditions : controlled expansion, no shrinkage, high thermal shock resistance and high mechanical strength. These specifications makes Andalusite very useful for refractory lining.

Our run of mine range is used for standard refractory applications especially shaped refractory.

	RANDALUSITE™	PURUSITE™	KERPHALITE KA™	KERPHALITE KB™
SIZE / PRESENTATION	1 - 4 mm 3 - 8 mm	0 - 4 mm	0,3 - 1,6 mm	0,3 - 1,6 mm
CHEMICAL ANALYSIS (%)				
Al ₂ O ₃	59,5	58,9	58,7	53,6
Fe ₂ O ₃	0,70	0,80	1,05	1,35
Na ₂ O	0,10	0,10	0,10	0,15
K ₂ O	0,20	0,35	0,35	0,45

These figures are only typical datas. Specifications/Individual. Technical data sheets are available upon request.

The technical information and specifications contained in this data sheet are only for information purposes. These information and specifications can be modified and do not constitute nor could be constitutive or be interpreted as a representation and/or as a warranty of the validity of the information and specifications specified. The general terms and conditions of sale, available on our website or upon request from our customer service, apply to the sale of our products.

